TN-79

CLEAR ACRYLIC WATERPROOF SEALER



PRODUCT CODE: 2324-C

GENERAL DESCRIPTION

TEN TN-79 is a high-quality acrylic waterproof sealer, designed to provide a durable and resistant seal on multiple surfaces. Its transparent formula preserves the substrate's original appearance, making it ideal for construction, maintenance, and infrastructure applications.

RECOMMENDED APPLICATIONS AND USES

Compatible Surfaces:

- Masonry.
- Concrete and mortar
- Metal.
- Wood
- Insulation layers

Areas Of Application:

- Roofs, walls, and floors.
- Residential housing, bathrooms, and underground works.
- Tunnels, bridges, swimming pools, and water tanks.

DIRECTIONS FOR USE

Surface Preparation::

- Clean the surface thoroughly.
- Remove all dust, grease, and any other contaminants.

Application:

- Use a brush (camel hair) or a roller (nap or microfiber).
- Apply evenly.

Drying:

- Tack-free: 45 seconds to 1 minute (at 24.6°C and 60% RH).
- Entre capas: esperar de 2 a 4 horas antes de reaplicar.

Recomendación:

- Aplicar una segunda capa para máxima efectividad.
- Between coats: Wait 2 to 4 hours before reapplying.

STORAGE

- Store in a cool, dry, and well-ventilated place.
- Avoid exposure to heat sources or ignition points.
- Keep the container tightly sealed.

PRESENTATION AND PACKAGING

- **Standard Presentation:** Heavy-duty plastic bucket with a hermetic lid.
- **Capacity:** 5 Liters.

PIC DISTRIBUIDORA

Contact:
Phone: +1 (956) 435-4262
Mail: info@picgrupo.com

GRUPO PIC
picgrupo.com

TN-79

CLEAR ACRYLIC WATERPROOF SEALER



PRODUCT CODE: 2324-C

TECHNICAL SPECIFICATIONS

Appearance:	**Semi-fluid paste, free of lumps and bubbles.**	Curing Speed:	**5 mm / 24 h**
		Elastic Recovery:	**>100%**
Color:	**Transparent**	Elongation at Break:	**438%**
Density:	**1.1 g/cm³**	Rotational Resistance:	**1.6**
Solids Content:	**86%**		
Tack-Free Time:	**45 sec a 1 min . (24.6 °C / 60% HR)**		

SAFETY PRECAUTIONS

Personal Protective Equipment (PPE):

- Gloves, safety goggles, and face mask.
- Use in well-ventilated areas.

First Aid Measures:

- Skin Contact: Wash thoroughly with soap and water.
- Eye Contact: Rinse with plenty of water and seek medical attention.
- Inhalation: Move to a location with fresh air.

CHEMICAL COMPOSITION

COMPONENT	CONCENTRATION	HAZARDS	EXPOSURE LIMIT (GBZ 2.1-2019)
Water	40%	Not classified	-
Calcium carbonate	30%	Not classified	-
Butyl acrylate	25%	Skin and eye irritation sensitization.	PC-TWA: 25 mg/m³
Butyl acetate	4%	Respiratory irritation.	PC-TWA: 200 mg/m³ / PC-STEL: 300 mg/m³
Toluene	1%	Reproductive toxicity, irritation.	PC-TWA: 50 mg/m³ / PC-STEL: 100 mg/m³

PIC DISTRIBUIDORA

Contact:
Phone: +1 (956) 435-4262
Mail: info@picgrupo.com

GRUPO PIC
picgrupo.com